General Aplications: Electroplating, discoloration and liquid deodorization ...

**Physical Features:** Approx 30% carbon content.

<b>Physical Properties</b>		UnitsTest	Method	<b>Average Obtained</b>
Grammage		grs/m²	ISO 536	155
Thickness	1KPa	μm	ISO 534	300
Burst Strength	Dried	Kpa	ME/020	>150
Burst Strength	Wet	Kpa	ME/020	>60
Permeability Δp	20 cms/s	mmWc	ME/010	140-240
Burst Strength		mmWc	ME/015	200-290
Filtration Speed	(*)	μm	ME/015	30
Middle Pore	(*)	μm	ME/015	10

Tolerance + / - 10%

(\*) Results obtained using a mathematical correlation.

The results of our tests are "Internal methods" of Dorsan filtration, S.L. in typical production batches.

The information provided in this document is only a guide and should not be considered as a guarantee.

All implied warranties are expressly excluded, including without limitation, any warranty for commercial or fitness for use.

All users of this filter media are responsible for ensuring that it is appropriate for its requirements of use and correct destination

final and recycled in the environment.

We reserve the right to change information without notice.

Dorsan® is a registered trademark of Dorsan filtration, S.L. All trademark rights are reserved.

Note. We reserve the right to change these informations without any previous notice.

Nota. Nos reservamos el derecho a modificar la información que aparece en este folleto sin previo aviso.



