**General Aplications:** Electroplating, Chemical-Pharmaceutical.

Physical Features: Smooth Surface

<b>Physical Properties</b>		Units	<b>Test Method</b>	Average Obtained
Grammage		g/m2	ISO 536	490
Thickness	50KPa	mm	ISO 534	2.00
Permeability		s/300mL	ME/010	12
Burst Strength		Кра	ME/015	+90
Colour			ME/015	Black
Carbon Contain			ME/015	+ 40%

(\*) Results obtained using a mathematical correlation. The results of our tests are "Internal methods" of Dorsan filtration, S.L. in typical production batches.

High Activated Granulated Carbon Cellulose Pulp 186.1673 Wet Strength Resin 176.170 and 176.180

The information provided in this document is only a guide and should not be considered as a guarantee. All implied warranties are expressly excluded, including without limitation, any warranty for commercial or fitness for use. All users of this filter media are responsible for ensuring that it is appropriate for its requirements of use and correct destination final and recycled in the environment. We reserve the right to change information without notice.

Dorsan® is a registered trademark of Dorsan filtration, S.L. All trademark rights are reserved.

Note. We reserve the right to change these informations without any previous notice.

Nota. Nos reservamos el derecho a modificar la información que aparece en este folleto sin previo aviso.



